

Mold Release Film



- ✓ Stable and superior molding performance.
- ✓ Excellent gas barrier property from the molding resin and heat-resisting of 180°C
- ✓ The processing of roughness inside, the removal performance is excellent.

Item		SV-3804M
Structure		<ul style="list-style-type: none"> ← Ac Adhesive & Antistatic side ← Polyester Film ← Matt Side
Thickness (μm)	Total	42
Tensile Strength (Mpa)	MD	65
	TD	65
Elongation (%)	MD	50
	TD	50
Surface Profile (μm)	Ra	0.66
	Rz	2.0
Heat Shrinkage (%)	-	0.1
Surface Resistivity (Ω/□)		10 ⁹
180° Peel Strength	RT	2
	175°C x 10min	10

Mold Release Film Process

